




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B29C 45/14	A1	(11) International Publication Number: WO 99/20450 (43) International Publication Date: 29 April 1999 (29.04.99)
(21) International Application Number: PCT/US98/21140 (22) International Filing Date: 7 October 1998 (07.10.98) (30) Priority Data: 197 45 919.6 17 October 1997 (17.10.97) DE (71) Applicant (for all designated States except US): MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, Saint Paul, MN 55133-3427 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): BECK, Roland [DE/DE]; Engelblecker Strasse 133, D-41066 Mönchengladbach (DE). (74) Agents: BOND, William, J. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).		(81) Designated States: CA, JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report.

(54) Title: INJECTION MOLD FOR INSERT-MOLDING A SYNTHETIC MATERIAL AROUND A FILTER MATERIAL, FILTER FOR THE FILTRATION OF FLUIDS AND METHOD FOR PRODUCING SUCH FILTER

(57) Abstract

The injection mold for insert-molding a synthetic material around the edge of a filter material comprising at least one particle filter layer and at least one active carbon layer of active carbon particles, is provided with a first mold half (28) and a second mold half (30) which comprise mutually confronting mold walls (32, 34). In their assembled state, the two mold halves (28, 30) define a receiving space (36) for the filter material (12), a molding space (42) for accommodating the edge (14) of the filter material (12) and for forming the synthetic material (74) to be arranged by insert molding



around the edge (14) of the filter material (12), with at least one injection channel (44) entering the molding space (42), and a transition space (38) arranged between the receiving space (36) and the molding space (42) for accommodating the edge portion (40) of the filter material (12) adjacent the edge (14) of the filter material (12). The transition space (38) is formed with a constricted portion (46) for preventing the leakage of synthetic material (74) from the molding space (42) into the receiving space (36). The constricted portion (46) comprises at least two narrowed portions (60) with a widened portion (62) arranged therebetween, the distance of the mold walls (32, 34) of the two mold halves (28, 30) being smaller in the narrowed portions (60) than in the widened portion (62). The two narrowed portions (60) and the widened portion (62) are arranged respectively transversely to that direction of the transition space (38) which is oriented between the molding space (42) and the receiving space (36).

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Injection mold for insert-molding a synthetic material around a filter material, filter for the filtration of fluids and method for producing such filter

5 The present invention relates to an injection mold for insert-molding a synthetic material around the edge of a filter material used particularly for the filtration of air streaming into the interior of a motor vehicle. Further, the invention relates to a method for producing a filter for the filtration of fluids, as used particularly in vehicles. Finally, the invention relates to a filter for the filtration of fluids.

10 For improving the function of filters for the cleaning of a fluid flow, i.e. particularly of an air flow, increasing use is made of active carbon filters, apart from conventional particle filters. For easy handling during the production of such filters, it is suitable to use filter materials which, in addition to at least one particle filter layer, also comprise an active carbon layer of active carbon particles. For improved convenience during the assembly of filters, the filter materials of the filters are connected - at least
15 along parts of their edges - to stiffening elements which are particularly provided as frames surrounding the edge of the filter material. Such frames or stiffening elements fulfill a holding function because, if the filter material is folded into a zig-zag shape for enlarging the filter surface, they will maintain the corrugated structure of the filter surface.

20 The attachment of stiffening elements or a continuous frame to a filter material is realized in a cost-saving manner by molding a synthetic material around the filter material. For this purpose, the filter material is inserted into an injection mold, with the edge of the filter material projecting into a molding space of the injection mold and the rest of the filter material being arranged in a receiving space of the injection mold. Now, to prevent the leakage of synthetic material into the receiving space when injecting the synthetic
25 material into the receiving space, the injection mold must be in sealing abutment on the filter material so that no fluid connection between the molding space and the receiving space exists for the viscous synthetic material. The molding of synthetic material around a filter material is difficult particularly if, due to the structure of the filter material, a tightly sealed closure between the molding space and the receiving space can be realized not at all
30 or only by extreme pressure forces acting on the filter material. This is the case, e.g., when the filter material, in addition to a particle filter layer, also comprises an active carbon

layer of active carbon particles or has porous properties. The porous structure of an active carbon layer requires the application of relatively high press-on forces which, in the region between the molding space and the receiving space, are exerted by the injection mold onto the filter material to thus squeeze off the filter material, as it were. These high force cause considerable wear of the injection mold so that the cost-saving effects obtainable by the molding technology are partially neutralized due to increased expenses for injection molds.

It is an object of the invention to provide an injection mold for insert-molding a synthetic material around the edge of a filter material comprising at least one particle filter layer and at least one active carbon layer of active carbon particles, wherein the region between the molding space and the receiving space is tightly sealed against leakage of the viscous synthetic material in the direction towards the filter material, with only minimum press-on forces being required.

For solving the above object, the instant invention provides an injection mold for insert-molding a synthetic material around the edge of a filter material, in particular a filter material comprising at least one particle filter layer and at least one active carbon layer of active carbon particles, said injection mold comprising

a first mold half and a second mold half, comprising mutually confronting mold walls which in the assembled state of the two mold halves define the following cavities therebetween:

a receiving space for the filter material,

a molding space for accommodating the edge of the filter material and for forming the synthetic material to be molded around the edge of the filter material, at least one injection channel entering the molding space, and

a transition space arranged between the receiving space and the molding space for accommodating the edge portion of the filter material adjacent the edge of the filter material, wherein

the transition space is formed with a constricted portion for preventing the leakage of synthetic material from the molding space into the receiving space,

the constricted portion comprises at least two narrowed portions with a widened portion arranged therebetween, the distance of the mold walls of the two mold halves being smaller in the narrowed portions than in the widened portion, and

5 the two narrowed portions and the widened portion are arranged respectively transversely to that direction of the transition space which is oriented between the molding space and the receiving space.

The injection mold of the invention comprises two mold halves which, in the
10 closed condition, form a receiving space for the filter material, a molding space for forming the synthetic material to be molded around the edge of the filter material, and a transition space between the receiving space and the molding space. The filter material to be subjected to insert molding is placed into the receiving space, with the edge portion of the filter material extending through the transition space up to the molding space. Thus,
15 the actual edge of the filter material projects from the transition space into the molding space. Arranged within the transition space is a constricted portion formed by the walls of the two mold halves; within this constricted portion, the mold walls of the mold halves are arranged in fluid-tight abutment on the filter material when the latter has been inserted.

According to the invention, the constricted portion of the transition space
20 comprises at least two narrowed portions and a widened portion arranged therebetween. In each of the narrowed portions, the distance of the mold walls of the two mold halves is smaller than in the widened portion. In this manner, the two mold halves together with the inserted filter material provide a fluid-tight closure, formed in the manner of a labyrinth seal, against the synthetic material injected in a liquid state. The at least two narrowed
25 portions, which are arranged transversely to that direction of the transition space which is oriented between the molding space and the receiving space and, when viewed along the direction of the transition space are arranged behind each other between the molding space and the receiving space, act like two barriers for preventing the intrusion of viscous synthetic material from the molding space into the receiving space.

30 Because of the provision of a plurality of narrowed portions, the two mold halves in these narrowed portions need abut the filter material only with a lower press-on force to

realize a fluid-tight closure between the molding space and the receiving space. The widened portion arranged between respectively two narrowed portions serves for accommodating filter material which has been laterally displaced due to squeezing in the narrowed portions. Thus, in the invention, active carbon particles (in as far as they are not
5 decreased in size when squeezing the filter material) are urged from the edge zones of two adjacent narrowed portions into the widened portion arranged therebetween. Further, the widened portion or each of the plurality of widened portions functions like a dead volume for receiving viscous synthetic material which, during the molding process performed on the edge of the filter material (possibly still) passes through the narrowed portion on the
10 side of the molding space.

Preferably, a highly reliable production with an almost negligible percentage of rejects is realized by providing the constricted portion of the transition space with three narrowed portions with intermediate widened portions, with the narrowed portions and the widened portions being arranged alternately in that direction of the transition space which
15 is oriented between the molding space and the receiving space.

In a further preferred embodiment of the invention, also the molding space is provided with at least one constricted portion dividing the molding space into a first partial space and a second partial space. This constricted portion of the molding space increases the flow resistance to the injected synthetic material. The edge of the filter material
20 projects into that partial space of the molding space which follows the transition space, and the injection channel or the injection channels for injecting the synthetic material into the molding space enter into the other partial space of the molding space. By this arrangement, a flow gradient directed to the edge of the filter material is generated within the molding space. As a result, it can be safeguarded within in certain limits - that, when
25 injecting the synthetic material, that partial space of the molding space which has the injection channels entering therein will be filled first. Only thereafter, the front of the viscous synthetic material passes the constricted portion to enter the other partial space of the molding space which has the edge of the filter material projecting therein. Thereby, in turn, it is accomplished that the synthetic material will primarily flow from the partial
30 space comprising the injection channels into the partial space receiving the edge of the filter material, instead of flowing in the reverse direction. In this manner, a "washing out"

of the edge of the filter material, i.e. a detachment of active carbon particles from the edge of the filter material, is largely prevented, which has a favorable effect for the design of the finished filter because no or nearly no active carbon particles will penetrate into the synthetic-material element molded around the filter material. The injection mold of the invention is particularly suited for insert molding a synthetic material around filter materials which comprise an active carbon layer of active carbon particles arranged between two nonwoven layers. In such a configuration, one of the two nonwoven layers functions as a particle filter layer and is preferably formed from an electret material. This electret material preferably comprises synthetic fibers of polypropylene which have been given electret properties. While that layer of the filter material which serves as a particle filter layer is arranged before the active carbon layer when viewed in the flow direction, the second nonwoven layer is arranged behind the active carbon layer and is particularly provided to keep the active carbon particles from being detached and carried along with the fluid flow to be filtered.

An inventive filter for the filtration of fluids, provided with a synthetic material therearound by an insert molding process using the inventive injection mold, comprises

a filter material having upper and lower sides and a limiting edge, in particular a filter material comprising at least one particle filter layer and an active carbon layer of active carbon particles,

a frame surrounding the limiting edge and having the limiting edge of the filter material embedded therein, and

at least two deepened grooves having a rib arranged therebetween and being arranged adjacent to the frame and substantially parallel to the direction of the frame at least in a part of the upper side and/or the lower side of the filter material.

The inventive filter is distinguished particularly by the provision of two deepened grooves in the frame-side region of the filter material, with a rib formed between the two deepened grooves. The at least two deepened grooves and the rib arranged therebetween are arranged substantially in parallel to the direction of at least one portion of the (synthetic) frame (attached by insert molding).

Corresponding to the number of narrowed portions within the constricted portion of the transition space of the injection mold, the filter in the frame-side region of its filter

material comprises a plurality of deepened grooves with respective ribs arranged therebetween.

In a preferred embodiment of the inventive filter, the frame has a reduced thickness in the region of the embedded edge of the filter material. This narrowed portion of the frame corresponds to the narrowed portion of the molding space of the injection mold that has been used for producing the inventive filter.

A preferred embodiment of the filter according to the invention and an embodiment of the injection mold according to the invention will be described hereunder in greater detail with reference to the drawings.

Fig. 1 shows a perspective view of a filter comprising a filter material with two non-woven layers and an active carbon layer arranged therebetween, and a frame of synthetic material molded around the filter material.

Fig. 2 shows a sectional view along the line II-II of Fig. 1,

Fig. 3 shows a sectional view along the line II-II of Fig. 1, wherein the filter material of the filter according to Fig. 1 is arranged between the two halves of an injection mold for molding synthetic material around the filter material and the two halves of the injection molded are not yet fully moved into their closed condition,

Fig. 4 shows a sectional view similar to Fig. 3 in the closed condition of the injection mold.

Fig. 5 shows a view similar to Fig. 4 wherein, however, that partial space of the frame-forming molding space which follows the injection channel or the injections channels is already filled with injected synthetic material.

Fig. 6 shows a sectional view similar to Fig. 5 wherein, however, the whole molding space is filled with synthetic material.

Fig. 7 shows an enlarged view of the region VII of Fig. 2 for better illustration of the transition space between the frame and the therein embedded filter material of the filter according to Fig. 1.

Figs. 1, 2 and 7 show full or partial views of a filter element 10 which, by means of an injection mold according to Figs. 3 to 6 has been provided with a frame structure of a synthetic material arranged therearound by insert molding. Filter element 10 comprises a three-layered filter material 12 arranged in zig-zag-shaped or wave-shaped folds. The edge

14 of filter material 12 is surrounded by a continuous frame 16 of a synthetic material having the edge 14 of the filter material embedded therein. In this manner, a tight mechanical connection is established between the frame 16 and the filter material 12, with the frame 16 supporting the zig-zag or wave structure of filter material 12.

5 As shown in Figs. 2 and 7, the filter material 12 comprises a filtering non-woven layer 18. This filtering non-woven layer 18 acts like a particle filter and comprises individual fibers of a synthetic material with electret properties. Arranged on the filtering non-woven layer 18 is an active carbon layer 20 of active carbon particles. This active carbon layer 20 functions like a deodorizing filter and will trap, e.g., harmful substances
10 from the fluid - particularly air - which is to be filtered. on the side of the active carbon layer 20 facing away from the filtering non-woven layer 18, a cover non-woven layer 22 of synthetic fibers is arranged. The thickness of the cover non-woven layer 22 is substantially smaller than the thickness of the filtering non-woven layer 18. Further, the cover nonwoven layer 22 has a considerably larger stiffness than the filtering non-woven layer
15 18. In Figs. 2 and 7, the direction of the fluid flow to be filtered by the filter 10 is indicated by an arrow at 24. As evident therefrom, the filtering non-woven layer 18 in the flow direction 24 is arranged before the active carbon layer 20 which in turn has the cover non-woven layer 22 arranged therebehind. Thus, the purpose of cover non-woven layer 22 resides primarily in preventing a detachment of particles of the active carbon layer 20 and
20 lending support to the active carbon layer 20 as a whole.

For producing the frame 16 of synthetic material, the three-layered filter material 12 is inserted into the injection mold 26, partially shown in Fig. 3 in sectional view, which comprises an upper mold half 28 and a lower mold half 30. Both mold halves 28,30
25 comprise mutually confronting mold walls 32,34 forming spaces therebetween which will be described in greater detail hereunder.

In the central region of the injection mold, the two mold halves 28,30 define a wave-like receiving space 36 therebetween for receiving the filter material 12.

Towards the edge of filter material 12, the receiving space 36 is followed by a transition space 38 having the edge portion 40 extending therethrough. The end of
30 transition space 38 facing away from receiving space 36 is followed by a molding space 42 whose configuration will define the shape of frame 16. The edge 14 of filter material 12

projects from transition space 38 into molding space 42. Injection channels 44, extending through upper mold half 28, enter into molding space 42.

By means of the injection mold 26 as partially shown in Fig. 3, a synthetic material, e.g. polypropylene, can be arranged by insert molding around the filter material 12 on the edge 14 of the filter material. When thus insert-molding a synthetic material around the part inserted into an injection mold - in the instant case, the filter material 12 - it is imperative that the injected synthetic material will not penetrate into all of the regions of the inserted part, i.e. the filter material 12. Thus, when the injection mold has been moved into its closed condition, a tight closure must be obtained between the two mold halves 28,30 on the one hand and the filter material 12 on the other hand to thus provide a fluid-tight sealing for the injected synthetic material. This causes problems especially when using the filter material 12 discussed here, due to the active carbon layer. This problem could be solved by selecting a correspondingly high force for pressing the two mold halves onto the filter material 12 in the edge portion 40, which, however, would subject the filter material to a considerable squeeze-off effect. High press-on forces, however, cause an increased wear of the injection mold 26.

In the injection mold 26 as described herein and illustrated in the Figures, a fluid-tight closure between the two mold halves 28,30 on the one hand and the filter material 12 on the other hand is realized by providing the transition space 38 with a constricted portion 46 within which the mold walls 32,34 are formed with projections 48,50. While the projection 48 of the upper mold half 28 is of a substantially trapezoidal shape and has a continuous, flat outer face 52 directed towards the lower mold half 30, the outer side 54 of the projection 50 of the lower mold half 30 is formed with three mutually parallel, longitudinal ribs 56 with deepened portions 58 arranged therebetween. The ribs 56 and the deepened portions 58 run along the direction of the edge portion 40 and the edge 14 of filter material 12, respectively. In the closed condition of the injection mold (cf. Fig. 4), the edge portion 40 of filter material 12 is heavily compressed by the ribs 56 along three zones. The height of the ribs 56 is selected in accordance with the nature (compressibility and composition) of the synthetic material and the injection pressures of the synthetic material in such a manner that, in these zones, there will be generally a tight abutment of the two mold halves 28,30 on the filter material 12. As shown in Fig. 4, the ribs 56 act on

the filtering non-woven layer 18, while the projection 48 of the upper mold half 28 acts on the cover non-woven layer 22 of the filter material 12. By the increased press-on force in the narrowed portions 60 formed by the ribs 56 in the constricted portion 46 of the transition space 38, also the active carbon layer 20 arranged between the non-woven layers 18 and 22 is compressed. The deepened portions 58 arranged between the ribs 56 define widened portions 62 which can serve for accommodating filter material displaced in the narrowed portions 60.

As is best seen in Fig. 4, the molding space 42 is provided at 64 with a constriction (narrowed portion) provided as a reduction of cross-section and formed by mutually confronting projections 66,68 of the mold walls 32,34 of the two mold halves 28,30. By this constriction 64 or narrowed portion, the molding space 42 is divided into first and second partial spaces 70,72. In this arrangement, the second partial space 72 forms the connecting space between the first partial space 70 of the molding space 42 and the transition space 38. This second partial space 72, which thus joins the transition space 38 while arranged opposite to the receiving space 36, has the edge 14 of the filter material projecting thereinto. The injection channels 44 enter into the first partial space 70 of molding space 42. On the whole, the shape of the molding space 42 resembles a U of which one leg has its free end is formed by the second partial space 72.

With reference to Figs. 3 to 6, the process of producing the filter element 10 will be explained hereunder.

First, the three-layered filter material 12 is folded into a zig-zag-shape and placed into the lower mold half 30 of the injection mold 26. Subsequently, the upper mold half 28 is moved against the lower mold half 30, thus closing the injection mold 26 (cf. Fig. 4). In this condition, the filter material 12, except for its edge portion 40, is arranged in the receiving space 36 of injection mold 26. The edge portion 40 of the filter material 12 extends through the transition space 38 up to the molding space 42, with the actual edge 14 of the filter material 12 projecting into the second partial space 72 of molding space 42. The two mold halves 28,30 can be brought to a suitable temperature so that the injected synthetic material will not cool down too much during the actual injection process.

Starting from the situation according to Fig. 4, synthetic material 74 is now injected into the molding space 42 through the injection channels 44. In the region of the

constriction or narrowed portion 64, the molding space 42 offers an increased flow resistance. As a result, initially, primarily the first partial space 70 will be filled with synthetic material 74. Only when the first partial space 70 has been substantially filled with synthetic material 74 (cf. Fig. 5), synthetic material 74 will enter also into the second partial space 72. Thus, the oncoming flow of the injected synthetic material 74 will spread substantially unidirectionally in the direction of the second partial space 72 and within space 72. Therefore, the amount of synthetic material 74 flowing back again from the second partial space 72 into the first partial space 70 is negligible. This offers the advantage that practically no turbulences, which might cause a "washing" on the edge 14 of the filter material 12, will occur in the second partial space 72. Due to the narrowed portions 60 of the transition space 38, the synthetic material reaching the second partial space 72 is prevented from entering the transition space 38 to any noteworthy extent. Even if synthetic material 74 still passes the first narrowed portion 60 of transition space 38 on the side of the molding space, this synthetic material will be trapped by the widened portion 62 adjacent this narrowed portion. Already the provision of at least two narrowed portions 60 will almost completely exclude a leakage of injected synthetic material 74 beyond the second narrowed portion 60 into the transition space 38. Thus, at the end of the injection process, the situation will be as depicted in Fig. 6. In this condition, the edge 14 of filter material 12, projecting into the second partial space 72 of molding space 42, is enclosed by synthetic material 74. In other words, this means that the filter material 12 along its edge 14 is embedded in synthetic material 74. When the synthetic material 74 has solidified, the two mold halves 28,30 are moved apart, and the filter material 12 along with the synthetic material molded therearound, i.e. the filter element 10, is removed from the injection mold 26. The solidified synthetic material 74 will then form the edge 14 of the filter material.

Thus, according to Fig. 7, the filter material has its edge portion 40 formed with depressions shaped as deepened grooves 76, with raised portions shaped as ribs 78 arranged therebetween. This structure is generated by a corresponding shape of the mold wall 34 of the lower mold half 30 in the constricted portion 46. The edge 14 of the filter material 12 is embedded on the free end 80 of one leg of the substantially U-shaped frame

16. This free end 80 is connected to the remaining part 84 of the frame 16 through a constricted portion 80 of reduced diameter.

Claims

1. An injection mold for insert-molding a synthetic material around the edge of a filter material, in particular a filter material comprising at least one particle filter layer and at least one active carbon layer of active carbon particles, said injection mold comprising

a first mold half (28) and a second mold half (30), comprising mutually confronting mold walls (32,34) which in the assembled state of the two mold halves (28,30) define the following cavities therebetween: - a receiving space (36) for the filter material (12),

a molding space (42) for accommodating the edge (14) of the filter material (12) and for forming the synthetic material (74) to be insert-molded around the edge (14) of the filter material (12), at least one injection channel (44) entering the molding space (42), and

a transition space (38) arranged between the receiving space (36) and the molding space (42) for accommodating the edge portion (40) of the filter material (12) adjacent the edge (14) of the filter material (12), wherein

the transition space (38) is formed with a constricted portion (46) for preventing the leakage of synthetic material (74) from the molding space (42) into the receiving space (36),

the constricted portion (46) comprises at least two narrowed portions (60) with a widened portion (62) arranged therebetween, the distance of the mold walls (32,34) of the two mold halves (28,30) being smaller in the narrowed portions (60) than in the widened portion (62), and

the two narrowed portions (60) and the widened portion (62) are arranged respectively transversely to that direction of the transition space (38) which is oriented between the molding space (42) and the receiving space (36).

2. The injection mold according to claim 1, characterized in that the constricted portion (46) comprises three narrowed portions (60) and two widened portions (62) arranged respectively between adjacent narrowed portions (60).

3. The injection mold according to claim 1 or 2, characterized in that the molding space (42) is provided with at least one narrowed portion (64) for generating a flow gradient for the injected synthetic material (74) directed to the edge (14) of the filter material (12), that the at least one narrowed portion (64) of the molding space (42) divides the molding space (42) into a first partial space (70) and a second partial space (72), and that the at least one injection channel (44) enters into the first partial space (70) of the molding space (42), and the second partial space (72) of the molding space (42) is provided for receiving the edge (14) of the filter material (12).
4. The injection mold according to any one of claims 1 to 3, characterized in that the constricted portion (46) of the transition space (38) is formed by alternately arranged ribs (56) and deepened portions (58) in at least one of those two regions of the mold walls (32,34) of the mold halves (28,30) which define the constricted portion (46).
5. The injection mold according to any one of claims 1 to 4, characterized in that the receiving space (36) is wave-shaped.
6. A method for producing a filter comprising a filter material, in particular a filter material including at least one particle filter layer and at least one active carbon layer of active carbon particles, by injection molding using an injection mold according to any one of claims 1 to 5, said method comprising the following steps:
- placing the filter material (12) into one of the two mold halves (28,30) of the injection mold (26),
- closing the injection mold (26) by moving the two mold halves (28,30) towards each other, wherein the filter material (12) is arranged in the receiving space (36), the edge portion (40) of the filter material (12) adjacent the limiting edge (14) extends through the transition space (38), and the edge (14) of the filter material (12) projects into the molding space (42),

injecting flowable synthetic material (74) through the at least one injection channel (44) into the molding space (42),

solidifying the synthetic material (74) filling the molding space (42), opening the injection mold (26) by moving the mold halves (28,30) away from each other, and removing the filter material (12) and the solidified synthetic material (74) forming the frame (16).

7. A filter for the filtration of fluids, comprising

a filter material (12) having upper and lower sides and a limiting edge (14), in particular a filter material comprising at least one particle filter layer (18) and an active carbon layer (20) of active carbon particles, a frame (16) surrounding the limiting edge (14) and having the limiting edge (14) of the filter material (12) embedded therein, and at least two deepened grooves (76) having a rib (78) arranged therebetween and being arranged adjacent to the frame (16) and substantially parallel to the direction of the frame (16) at least in a part of the upper side and/or the lower side of the filter material (12).

8. The filter according to claim 7, characterized in that three deepened grooves (76) and two ribs (78) are formed on the upper side and/or the lower side of the filter material (12), with a respective rib (78) being arranged between each pair of adjacent deepened grooves (76).

9. The filter according to claim 7 or 8, characterized in that the deepened grooves (76) and the rib (78) or the ribs (78) is/are formed in the particle filter layer (18) and/or the active carbon layer (20).

10. The filter according to claim 7 or 8, characterized in that the filter material (12) comprises a particle filter layer (18) and a cover nonwoven layer (22), the active carbon layer (20) being arranged therebetween.

11. The filter according to claim 10, characterized in that the deepened grooves (76) and the rib (78) or the ribs (78) are formed in the particle filter layer (18) or the cover non-woven layer (22).
- 5 12. The filter according to any one of claims 7 to 11, characterized in that the filter material (12) is wave-shaped.
- 10 13. The filter according to any one of claims 7 to 12, characterized in that the frame (16) comprises a narrowed portion (64) arranged between that part (80) of the frame (16) which accommodates the limiting edge (14) of the filter material (12) and the remaining part (82) of the frame.
- 15 14. A filter for the filtration of fluids, comprising a filter material, in particular a filter material including at least one particle filter layer and at least one active carbon layer of active carbon particles and having a limiting edge embedded in the frame, by use of an injection mold according to any one of claims 1 to 5.
- 20 15. A filter for the filtration of fluids, comprising a filter material, in particular a filter material including at least one particle filter layer and at least one active carbon layer of active carbon particles and having a limiting edge embedded in the frame, by use of an injection mold according to claim 6.

- 1 / 4 -

FIG.1








FIG.2

- 2 / 4 -





INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/21140

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B29C45/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 2 125 707 A (NIPPONDENSO CO) 14 March 1984	1,7,12
X	see the whole document ---	6
A	PATENT ABSTRACTS OF JAPAN vol. 13, no. 111 (C-577), 16 March 1989 & JP 63 287521 A (SHUJI HARADA), 24 November 1988	1,5,7,12
X	see abstract ---	6
A	PATENT ABSTRACTS OF JAPAN vol. 13, no. 143 (M-811), 7 April 1989 & JP 63 306266 A (NIPPON DENSO CO LTD), 14 December 1988	1,7,12
X	see abstract ---	6
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

3 February 1999

Date of mailing of the international search report

10/02/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bollen, J

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/21140

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 448 876 A (MINNESOTA MINING AND MANUFACTURING CO) 2 October 1991	1,7,12
X	see the whole document ---	6
A	DE 21 62 355 A (PUROLATOR FILTER GMBH) 20 June 1973	1,7,12
X	see the whole document ---	6
A	US 4 543 283 A (CURTZE EDWARD W ET AL) 24 September 1985 see figure 5 -----	1,2,4

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/21140

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 2125707	A	14-03-1984	JP 1668287 C	29-05-1992
			JP 2021845 B	16-05-1990
			JP 60012113 A	22-01-1985
			JP 1666684 C	29-05-1992
			JP 2018893 B	27-04-1990
			JP 59026120 A	10-02-1984
			AU 540096 B	01-11-1984
			AU 1749383 A	09-02-1984
			DE 3328218 A	09-02-1984
			US 4569813 A	11-02-1986
			US 4744902 A	17-05-1988
EP 0448876	A	02-10-1991	AU 636955 B	13-05-1993
			AU 7120291 A	03-10-1991
			CA 2036639 A	30-09-1991
DE 2162355	A	20-06-1973	NONE	
US 4543283	A	24-09-1985	AU 581661 B	02-03-1989
			AU 4280385 A	13-03-1986
			BE 902540 A	16-09-1985
			BR 8503518 A	22-04-1986
			CA 1243060 A	11-10-1988
			DE 3521115 A	13-03-1986
			FR 2569625 A	07-03-1986
			GB 2164080 A, B	12-03-1986
			JP 61066645 A	05-04-1986
			LU 85932 A	22-01-1986
			NL 8501622 A	01-04-1986
			SE 462846 B	10-09-1990
			SE 8502480 A	05-03-1986